

## Concrete Surface Finishes

Supplier	Brand
Texture Coatings of America, Inc. Ft. Lauderdale FL - Ft. Lauderdale, FL	Tex-Cote 300 Bridge Cote (fine texture) XL-70 Bridge Cote (fine texture)
The Euclid Chemical Company Cleveland, OH	Tammscoat (fine texture)
The Sherwin Williams Company Cleveland, OH	Concrete Texture Coating B97W155

### Method of Documentation of Acceptance:

By brand and source. Unless otherwise specified in the Contract, the color shall be concrete gray, equal or close to Shade 36622 of Federal Color Standard 595B.

### Method of Approval:

- The manufacturer will provide the Materials Division with the following:
  - Certified test results from a commercial, independent testing laboratory for freeze-thaw resistance,
  - Accelerated weathering,
  - Fungus growth resistance,
  - Chemical analysis of formulation, and physical properties.

Freeze-thaw resistance, accelerated weathering, and fungus growth resistance testing shall be performed according to AHTD Test Method 806:

**Freeze-Thaw Resistance - Cold storage at -0°F(-18°C) / Thawing at 60°F 80°F (16° C-27°C) for fifty (50) cycles. At the end of fifty cycles of the Freeze-Thaw test, the specimen shall show no visible defects.**

**Accelerated Weathering – Tested per ASTM G 153, Cycle 1 or ASTM 155, Cycle 1, for 5000 hrs. The specimen shall show no deleterious effects at 5000 hours when viewed under 5x magnification.**

**Fungus Growth Resistance – Minimum fungus resistance rating of 10 when tested**

## Concrete Surface Finishes

according to Federal Specification TT-P-29 and ASTM D 3273 with twenty-one (21) day minimum incubation period.

Retesting will be required whenever performance has been unsatisfactory or for a change in formulation.

- Sample(s) of the material along with an infrared spectra of the synthetic resin binder shall be furnished to the Materials Division for further testing and evaluation.
- When deemed necessary by the Materials Engineer, and at a frequency determined by him, random samples will be taken and may be tested for quality. Failure of these tests and/or unacceptable field performance as determined by the Department will be cause for removal of a product from this QPL.

No information contained in these lists is to be used for promotional purposes.

The manufacturer of privately labeled products must be disclosed.